

Application of natural polymers as pharmaceutical excipients

Tushar Saha *, Zia Uddin Masum, Shadhan Kumar Mondal, Md. Sakhawat Hossain, Md. Abu Jobaer, Rafiqul Islam Shahin, Titumeer Fahad

Department of Pharmacy, University of Dhaka, Bangladesh

Abstract

The use of natural polymer as excipients in pharmaceutical sector is expanding day by day. Low cost, safety issues, availability, bio-degradable are the main causes that make them differ from other sources. Natural sources have wide range of varieties and characteristics. So they can be used numerously in pharmaceutical products as excipients to serve the desired purposes. The aim of this article is to give an over view of the application of natural polymeric substances that can be used as excipients in pharmaceuticals.

Keywords: Natural polymer, Safe, Cost effective.

Citation: Saha T, Masum ZU, Mondal SK, Hossain MS, Jobaer MA, Shahin RI, Fahad T (2018) Application of Natural Polymers as Pharmaceutical Excipients, Global J Life Sci Biol Res 4:1. doi:10.24105/gjlsbr.2018.4.2

Received date: September 21, 2018; **Accepted date:** October 10, 2018; **Published date:** October 15, 2018

Copyright: © 2018 Tushar Saha. This is an open access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Competing Interests: The author has declared that no competing interests exist.

*E-mail: tushar.saha21@yahoo.com

Introduction

Excipients play an important role to convert the Active Pharmaceuticals Ingredient (API) in to dosage form by ensuring its safety and efficacy so that administration can be suitable for the patients [1]. The use of natural polymeric excipients in pharmaceutical sectors is increasing day by over semi synthetic or synthetic excipients [2]. Low toxicity, availability, cost effectiveness, soothing action, non-irritant nature are the main reasons which make them superior from others sources [3-6]. Natural polymeric excipients can be used in different formulations like solid, liquid and semi-solid dosage forms where they act as disintegrates, binders, film formers, matrix formers, release modifiers, thickeners, stabilizers, emulsifiers, suspending agents, sweetener and mucoadhesives agent [7]. Solid monolithic matrix systems, implants, films, beads, micro particles, nanoparticles, inhalable and injectable systems, viscous liquid can be formulated and manufactured by the help of natural polymeric excipients [8-10].

Characteristics of an ideal pharmaceutical excipient

Pharmaceutical excipient should have some certain characteristics. Natural polymeric substances should have to fulfil these characteristics in order to be a successful candidate as pharmaceutical excipient. These are as follows:

1. Pharmacologically inert but pharmaceutically active.
2. Nontoxic and non-irritant.
3. No interaction with drug or with other substances present in the formulation and packaging.
4. Ease of handling.
5. Feasible.
6. Cost effective and readily available.

List of excipients used in pharmaceutical preparation

Commonly used excipients which are used in

pharmaceutical preparations are: fillers, binders, disintegrants, coatings, sorbents, anti-adherent, lubricants, glidants, preservatives, antioxidants, flavoring agents, sweetening agents, coloring agents, solvent, co solvent, buffering agents, chelating agents, viscosity imparting agents, surface active agents and humectants.

Disadvantages of natural polymers

Although natural polymers have some superior advantages but some disadvantages are also present which should be taken under considerations. Most common disadvantages are:

1. Microbial contamination may be occurred.
2. Batch to batch variation is observed.
3. The rate of hydration is uncontrolled.
4. Viscosity of the formulation reduced during the storage.
5. Most of the natural polymers are seasonal.

Sources of natural polymers

Natural polymers can be obtained from one of the three sources. These are plants, microbes and animals. From these source, plants have the largest amount of polymeric substances as well as the varieties. Some polymeric substances are obtained from animal sources and very few are obtained from the microbes [2].

Types of natural polymeric excipients

Natural polymeric excipients may be categorized into the following classes [7].

1. Polysaccharides of the plant cell wall: These polymers are mainly obtained from plant cell wall and cellulose, hemicelluloses, pectin are the main polymers of this group.
2. Gums and mucilages: Gums and mucilages are natural plant hydrocolloids which can be further classified into anionic or nonionic polysaccharides. They may be salts of polysaccharides also.
3. Seaweed polysaccharides: Seaweeds are mainly

macroscopic, multicellular marine algae. Seaweed polysaccharides mainly include carrageenans, agar and alginates.

4. Microbial polysaccharides: These types of polymers are obtained by the fermentation of carbohydrate products mainly. This fermentation is performed by specific bacteria or fungus. Xanthan gum, pullulan etc. are in this category.
5. Animal polysaccharides: Natural gums can be obtained from animal sources which are classified in this group. Chitin and chitosan are mostly used animal polysaccharides.
6. Exudates gums: Exudates gums are viscous, sticky fluid which is obtained after cutting the plant. They are actually seal-off infected sections of the plant and help to reduce the loss of moisture because of the physical injury or by the attack of fungi. Acacia gum, tragacanth gum, locust bean gum etc. are in this class.
7. Inulin: Inulin is obtained from plant source like onion, garlic, artichoke and chicory. It is actually a polysaccharide stored in the plants. Chemically it is gluco-fructants and multiple monomers are present.
8. Starches: Starches are polymeric carbohydrates which have a large glucose units joined by glycosidic bonds.
9. Dextran: Dextran is complex branched glucan which have different chain length.
10. Cyclodextrins: Cyclodextrins are mainly cyclic oligosaccharides having six to eight glucose units and they are joined with α -1,4 glucosidic bonds.
11. Curdlan: It is a neutral and linear β -glucan having intra or inter chain linkages.
12. Scleroglucan: It is a branched homo polysaccharide having a main chain of (1-3) linked β -D glucopyranosyl units.
13. Rosin: It is low molecular weight oleoresin.

Application of natural polymers as excipients

Natural polymers can act numerously as excipients in pharmaceutical preparation. A list of natural polymers and their pharmaceutical application are given below:

S.I	Natural Polymers	Pharmaceutical application
1.	Cellulose	Binder, filler, diluents, thickening and viscosity imparting agent, compressibility enhancer [11].
2.	Hemicellulose	Stabilizer of the gel phase of tablet and release modifier [12].
3.	Pectin	Colon specific drug delivery, controlled release drug delivery, patch and transdermal drug delivery, nano particle drug formulation [13-16].
4.	Alginates	Suspending agent, stabilizer, coating material, gelating agent, bioadhesive, microsphere [17-22].
5.	Carageenans	Gelling agent, stabilizer, demulcent, laxative [23-25].
6.	Gum agar	Suspending agent, emulsifier, laxative, gelling agent, surgical lubricant, disintegrates, bacterial culture media [26].
7.	Xanthan gum	Suspending agent, emulsifier, stabilizer, sustained release agent, pellets [27-29].
8.	Gellan gum	Disintegrating agent, ophthalmic drug delivery, beads, floating <i>in-situ</i> gel [30-33].
9.	Pullulan	Insulin preservation [34].
10.	Acacia gum	Suspending agent, emulsifier, binder, demulcent, emollient, osmotic drug delivery system [35-37].
11.	Tragacanth gum	Suspending agent, emulsifier, demulcent, emollient, sustained release agent [38].
12.	Locust bean gum	Controlled release agent [39,40].
13.	Guar gum	Binder, disintegrating agent, thicker, emulsifier, laxative, sustained release agent, colon targeted drug delivery, cross-linked microsphere [41-47].
14.	Grewia gum	Binder, tablet property enhancer, improved drug release [48,49].
15.	Okra gum	Binder, suspending agent, control release, sustained release, film coating and bio-adhesive material [50-58].
16.	Kyaha gum	Binder [59].
17.	Moringaoleifer gum	Tablet physical characteristics enhancer [60].
18.	Irvingiagabonensis	Binder, emulsifier, suspending agent [61-63].
19.	Hakeagiibbosa gum	Muco-adhesive, sustained release property [64].
20.	Psyllium mucilage	Binder, controlled release property [65,66].
21.	Inulin	Colon specific drug delivery [67].
22.	Starch	Binder, disintegrant, aiding drug delivery, film coating material [68,69].
23.	Dextran	Colon specific drug delivery [70-72].
24.	Cyclodextrins	Colonic drug deliver [73].
25.	Curdlan	Stabilizer, gelling agent [74].
26.	Scleroglucan	Laxative in tablet coating, stabilizer, hydrogel former [75].
27.	Rosin	Microencapsulation, film former, coating material, sustained release property, nano particle drug delivery [76-79].
28.	Tamarind gum	Binder, emulsifier, suspending and sustaining agent, mucoadhesive drug delivery [80-82].
29.	Gum ghatti	Binder, emulsifier, suspending agent [83].
30.	Neem gum	Aqueous film coating material [84]
31.	Albizia gum	Binder [85].
32.	Cashew gum	Suspending agent [86,87].
33.	Cassia toragum	Binding agent [88].
34.	Bhara gum	Microencapsulation [89].
35.	Leucaena seed gum	Emulsifier, suspending agent, binder, disintegrating agent [90-94].
36.	Cordia gum	Sustaining agent [95].
37.	Mimosa pudica	Binder, disintegrating agent [96,97].

Conclusions

Natural excipients have certain advantages over other synthetic and semi synthetic excipients. So these excipients are getting preference day by day. Potential characteristics of them help the scientist to formulate better formulation. But, while working with these excipients or using them in dosage form, it should pass all the regulatory requirements. Experiments and researches should be done with natural excipients in order to get the most safe and suitable one for pharmaceutical application.

References

- Goswami S, Naik S. Natural gums and its pharmaceutical application. *J Sci Inn Res* 2014; 3:112-121.
- Dharmendra S, Surendra JK, Sujata M, Shweta S. Natural excipients: A review. *Int J Pharm Bio Arch* 2012;3:1028-1034.
- BeMiller JN. In Whistler RL (ed), *Industrial gums*. Academic Press, London 1959; 213-221.
- Kakrani HK, Jain NK. A study on binding properties of guggal gum. *Indian J Hospital Pharmacist* 1981;18:100-102.
- Bhunvara NS, Khorana ML. Studies on suspending properties of hyprophilaspinosa. *Indian Drugs* 1985; 22: 500-502.
- Kulkarni GT, Gowthamarajan K, Dhobe FY, Suresh B. Development of controlled release spheroids using natural polysaccharide as release modifier. *Drug Deliv* 2005;12:201-206.
- Ogaji IJ, Nep EI, Peter JDA. Advances in natural polymers as pharmaceutical excipients. *Pharm Anal Acta* 2011;3:1-16.
- Beneke CE, Viljoen AM, Hamman JH. Polymeric plant-derived excipients in drug delivery. *Molecules* 2009;14:2602-2620.
- Pandey R, Khuller GK. Polymer based drug delivery systems for mycobacterial infections. *Curr Drug Deliv* 2004;1:195-201.
- Chamarthy SP, Pinal R. Plasticizer concentration and the performance of a diffusion-controlled polymeric drug delivery system. *Colloids Surf Physiochem Eng Asp* 2008;331:25-30.
- Kibbe AH. *Handbook of pharmaceutical excipients*. The Pharmaceutical Press, Washington DC 2000
- Fan J, Wang K, Liu M, He Z. In vitro evaluations of konjacglucomannan and xanthan gum mixture as the sustained release material of matrix tablet. *Carbohydrate Polymer* 2008;73: 241-247.
- Sinha VR, Kumria R. Polysaccharides in colon-specific drug delivery. *Int J Pharm* 2001;224: 19-38.
- Sungthongjeen S, Pitaksuteepong T, Somsiri A, Sriamornsak P. Studies on pectins as potential hydrogel matrices for controlled release drug delivery. *Drug Dev Ind Pharm* 1999;25:1271-1276.
- Musabayane CT, Munjeri O, Matavire TP. Transdermal delivery of chloroquine by amidated pectin hydrogel matrix patch in the rat. *Renal Fail* 2003;25:525-534.
- Cheng K, Lim LY. Insulin-loaded calcium pectinate nanoparticles: Effects of pectin molecular weight and formulation pH. *Drug Dev Ind Pharm* 2004;30:359-367.
- Hodsdon AC, Mitchell JR, Devies CD. Structure and behavior in hydrophilic matrix sustained release dosage forms: the influence of pH on the sustained-release performance and internal gel structure of sodium alginate matrices. *J Control Release* 1995;33:143-152.
- Howard JR, Timmins P. Controlled release formulation. *US Patent* 1988.
- Seiyaku F. Sustained-release dilazep hydrochloride tablets containing sodium alginate. *Japan Patent* 1989.
- Viernstein H. Retarded-release drug tablet with alginic acid sodium alginate matrix. *Austrian Patent* 1988.
- Kesavan K, Nath G, Pandit JK. Sodium alginate based mucoadhesive system for gatifloxacin and

- its in vitro antibacterial activity. *Sci pharm* 2010;78:341-357.
22. Balasubramaniam J, Rao VU, Vasudha M, Babu J, Rajinikanth PS. Sodium alginate microspheres of metformin HCl: Formulation and in vitro evaluation. *Curr Drug Deliv* 2007;4:249-56.
 23. Ahmed BJ, Al-Ghazawi M. Sustained release characteristics of tablets prepared with mixed matrix of sodium carrageenan and chitosan: Effect of polymer weight ratio, dissolution media and drug type. *Drug Dev Ind Pharm* 2005;31:241-247.
 24. Bonferoni MC, Rossi R, Tamayo M. The employment of carrageenan in a matrix system: I. Sensitivity to dissolution medium and comparison with Na carboxymethylcellulose and xanthan gum. *J Control Release* 1993;26:119-127.
 25. Bonferoni MC, Rossi S, Tamayo M. The employment of carrageenan in a matrix system. II. carrageenan and hydroxypropyl methylcellulose mixtures. *J Control Release* 1994;30:175-182.
 26. John GL, Declan MD, James EK. The use of Agar as a novel filler for monolithic matrices produced using hot melt extrusion. *Eur J Pharm Biopharm* 2006;64:75-81.
 27. Kulkarni D, Dwivedi AK, Sarin JPS. Tamarind seed polyose: A potential polysaccharides for sustained release of verapamil hydrochloride as a model drug. *Indian J Pharm Sci* 1997;59:1-7.
 28. Dhopeswarkar V, Zatz JL. Evaluation of xanthan gum in the preparation of sustained release matrix tablets. *Drug Dev Indus Pharm* 1993;19:999-1017.
 29. Santos H, Veiga F, Pina ME, Sousa JJ. Compaction compression and drug release properties of diclofenac sodium and ibuprofen pellets comprising xanthan gum as a sustained release agent. *Int J Pharm* 2005;295:15-27.
 30. Antony PJ, Sanghavi NM. A new disintegrant for pharmaceutical dosage forms. *Drug Dev Ind Pharm* 1997;23:413-415.
 31. Rozier A, Mazuel C, Grove J, Plazonnet B. Functionality testing of gellan gum: A polymeric excipient material for ophthalmic dosage forms. *Int J Pharm* 1997;153:191-198.
 32. Kedzierewicz F, Lombry C, Rios R. Effect of the formulation on the in-vitro release of propranolol from gellan beads. *Int J Pharm* 1999;178:129-136.
 33. Rajnikanth PS, Balasubramaniam J, Mishra B. Development and evaluation of a novel floating in situ gelling system of amoxicillin for eradication of *Helicobacter pylori*. *Int J Pharm* 2007;335:114-122.
 34. Akiyoshi K, Kobayashi S, Shichibe S, Mix D, Baudys M. Self-assembled hydrogel nanoparticle of cholesterol-bearing pullulan as a carrier of protein drugs: complexation and stabilization of insulin. *J Control Release* 1998; 4:313-320.
 35. Shefter E. In C. R. Raymond, J. S. Paul, J. W. Paul (eds.), *Handbook of Pharmaceutical Excipients*. The Pharmaceutical Press and the American Pharmaceutical Association 2003; 1-2.
 36. Lu EX, Jiang ZQ, Zhang QZ, Jiang XG. A water-insoluble drug monolithic osmotic tablet system utilizing gum Arabic as an osmotic, suspending and expanding agent. *J Control Release* 2003;92:375-382.
 37. Beneke CE, Viljoen AM, Hamman JH. Polymeric plant-derived excipients in drug delivery. *Molecules* 2009;14:2602-2620.
 38. Owen SC. In Raymond CR, Paul JS, Paul JW (eds.), *Handbook of Pharmaceutical Excipients*. The Pharmaceutical Press and the American Pharmaceutical Association 2003;654-656
 39. Bangale GS, Stephen RB, Shinde GV, Umalkar DG, Rajesh KS. Formulation and evaluation of natural gum based matrix tablets for oral controlled delivery of nimodipine. *Indian J Pharma Edu Res* 2011;45:375-383.

40. Xiaohong MG, Michae JT, John NS. Influence of physiological variables on the in-vitro drug-release behavior of a polysaccharide matrix controlled-release system. *Drug Dev Ind Pharm* 2003;29:19-29.
41. Kale VV, Kashiwa R, Parida SK. Formulation and release characteristics of guar gum matrix tablet containing metformin HCl. *Int J Pharma Exp* 2004;75-80.
42. Khullar P, Khar RK, Agrawal SR. Evaluation of guar gum in the preparation of sustained-release matrix tablets. *Drug Dev Ind Pharm* 1998;24:1095-1099.
43. Kibbe AH. In C. R. Raymond, J. S. Paul, J. W. Paul (eds.), *Handbook of Pharmaceutical Excipients*. The Pharmaceutical Press and the American Pharmaceutical Association 2003; 271-273.
44. Heda A, Shivhare U. Study of some natural hydrophilic polymers as matrix forming materials for sustained release tablet formulation. *Int J Pharm Exp* 2004;69-74
45. Krishnaiah YSR, Latha K, Rao LN, Karthikeyan RS, Bhaskar P, Satyanarayana V. Development of colon targeted oral guar gum matrix tablets of albendazole for the treatment of helminthiasis. *Indian J Pharm Sci* 2003;65:378-385.
46. Krishnaiah YSR, Latha K, Rao LN, Karthikeyan RS, Bhaskar P, Satyanarayana V. Guar gum as a carrier for colon specific delivery: Influence of metronidazole and tinidazole on in vitro release of albendazole from guar gum matrix tablets. *J Pharm Sci* 2001;4:235-243.
47. Chourasia MK, Jain SK. Potential of guar gum microspheres for target specific drug release to colon. *J Drug Target* 2004;12:435-442.
48. Okafor IS, Chukwu A. The binding property of grewia gum in sodium salicylate tablets. *West African J Biol Sci.* 2003;14:9-21.
49. Audu-Peter JD, Isah S. Evaluation of grewia gum as binder in paracetamol tablet. *J Pharm Biores* 2007;4:68-73.
50. Tavakoli N, Ghasemi N, Taimouri R, Hamishehkar H. Evaluation of okra gum as a binder in tablet dosage forms. *Iran J Pharm Res* 2004;2:47.
51. Momoh MA, Akikwu MU, Ogbona JI, Nwachi UE. In vitro study of release of metronidazole tablets prepared from okra gum, gelatin gum and their admixture. *Bio Res* 2009;6:339-342.
52. Kalu VD, Odeniyi MA, Jaiyeoba KT. Matrix properties of a new plant gum in controlled drug delivery. *Arch Pharm Res* 2007;30:884-889.
53. Ogaji I, Nnoli O. Film coating potential of okra gum using paracetamol tablets as a model drug. *Asian J Pharm* 2010;4:130-134.
54. Attama AA, Adikwu MU, Amorha CJ. Release of indomethacin from bioadhesive tablets containing carbopol 941 modified with abelmuschusculentus (Okra) gum. *Boll Chim Farm* 2003;142:298-302.
55. Ogaji I. Some physicochemical properties of acetaminophen pediatric suspensions formulated with okra gums obtained from different extraction processes as suspending agent. *Asian J Pharm* 2011;5:15-20.
56. Nasipuri RN, Igwilo CI, Brown SA, Kunle OO. Mucilage from abelmuschusculentus (okra) fruits- a potential pharmaceutical raw material; part1; physicochemical properties. *J Pharm Res Dev*1996;1:22-28.
57. Femi-Oyewo MN, Adedokun MO, Olusoga TO. Evaluation of the suspending proerties of albiziazygia gum on sulphadimidine suspension. *Trop J Pharm Res* 2004;3:279-284.
58. Kalu VD, Odeniyi MA, Jaiyeoba KT. Matrix properties of a new plant gum in controlled drug delivery. *Arch Pharm Res* 2007;30:884-889.
59. Odeku OA, Itiola OA. Evaluation of the effects of khaya gum on the mechanical and release properties of paracetamol tablets. *Drug Dev Ind Pharm* 2003;29:311-320.

60. Singh AK, Panner SR, Sivakumar T. Isolation, characterization and formulation properties of a new plant gum obtained from mangiferaindica. *Int J Pharma Biomed Res* 2010;1:35-41.
61. Odeku OA, Patani B. Evaluation of dika nut mucilage (*Irvingiagabonensis*) as a binding agent in metronidazole tablet formulation. *Pharm Dev Technol* 2005;10:439-446.
62. Ndjouenkeu R, Akingbala J, Oguntimein G. Emulsifying properties of three African food hydrocolloids: Okra (*Hibiscus esculentus*), dika nut (*Irvingiagabonensis*) and kha (*Belschmiedia sp.*). *Plant Foods Hum Nutr* 1997;51:245-255.
63. Isimi CY, Kunle OO, Bangudu AB. Some emulsifying and suspending properties of the mucilage extracted from kernels of *irvingiagabonensis*. *Boll Chim Farm* 2000;139:199-204.
64. Alur HH, Pather SI, Mitra AK, Johnston TP. Evaluation of the gum from *hakeagibbosa* as a sustained-release and mucoadhesive component in buccal tablets. *Pharm Deve Technol* 1999;4:347-358.
65. Kulkarni GT, Gowthamrajan K, Rao BG, Suresh B. Evaluation of binding properties of *plantago ovate* and *trigonella foenumgraecummucilages*. *Indian Drugs* 2002;3:422-425.
66. Singh B, Chauhan N. Modification of psyllium polysaccharides for use in oral insulin delivery. *Food Hydrocolloids* 2009;23:928-935.
67. Vervoort L, Van den Mooter G, Augustijns P, Busson R, Toppet S. Inulin hydrogels as carrier for colonic drug targeting: I. Synthesis and characterization of methacrylated inulin and hydrogel formation. *Pharm Res* 1997; 14: 1730-1736.
68. Larionova NV, Ponchel G, Duchene D, Larionova NI. Biodegradable cross-linked starch/protein microcapsules containing proteinase inhibitor for oral protein administration. *Int J Pharm* 1999;189:171-178.
69. Krogars K, Antikainen O, Heinamaki J, Laitinen N, Yliruusi J. Tablet filmcoating with amylose-rich maize starch. *Eur J Pharm Sci* 2002;17:23-30.
70. Brondsted H, Hovgaard L, Simonsen J. Dextran hydrogels for colonspecific drug delivery. IV. Comparative release mechanism of hydrocortisone and prednisolone phosphate. *STP Pharma Sci* 1995;5:65-69.
71. Simonsen L, Hovgaard L, Mortensen PB, Brondsted H. Dextran hydrogels for colon-specific drug delivery: V. Degradation in human intestinal incubation models. *Eur J Pharm. Sci* 1996;3:329-337.
72. Hovgaard L, Brondsted H. Dextran hydrogels for colon-specific drug delivery. *J Control Release* 1995;36:159-166.
73. Flourie B, Molis, C, Achour L, Dupas H, Hatat C, Rambaud JC. Fate of β -cyclodextrin in the human intestine. *J Nutr* 1993;123:676-680.
74. Jezequel V. Curdlan: A new functional beta-glucan. *Cereal Foods World* 1998;43:361-364.
75. Corrente F, Matricardi P, Paolicelli P, Tita B, Vitali F, Casadei MA. Physical carboxymethylscleroglucan/calcium ion hydrogels as modified drug delivery systems in topical formulations. *Molecules* 2009;14:2684-2698.
76. Mandaogade PM, Satturwar PM, Fulzele SV, Gogte BB, Dorle AK. Rosin derivatives: Novel film forming materials for controlled drug delivery. *React Funct Polym* 2002;50:233-242.
77. Fulzele SV, Satturwar PM, Dorle AK. Study of the biodegradation and in vivo biocompatibility of novel biomaterials. *Eur J Pharm Sci* 2003;20: 53-61.
78. Nande VS, Barabde UV, Morkhade DM, Patil AT, Joshi SB. Synthesis and characterization of PEGylated derivatives of rosin for sustained drug delivery. *React Funct Polym* 2006;66: 373-1383.

79. Lee CM, Lim S, Kim GY, Kim DW, Joon HR, Lee KY. Rosin nanoparticles as a drug delivery carrier for the controlled release of hydrocortisone. *Bio Technol Lett* 2005;27:1487-1490.
80. Thierry N, George C, John F. Alginate and gellan gum as a tablet coating. US Patent 6326028 B1
81. Kulkarni GT, Gowthamarajan K, Dhobe RR, Yohanan F, Suresh B. Development of controlled release spheroids using natural polysaccharide as release modifier. *Drug Deliv* 2005.12:201-206.
82. Kulkarni D, Dwivedi AK, Sarin JPS, Singh S. Tamarind seed polyose: A potential polysaccharide for sustained release of verapamil hydrochloride as a model drug. *Indian J Pharm Sci* 1997;59:1-7.
83. Jain NK, Dixit VK. Studies on gums and their derivatives as binding agent. *Indian J Pharm Sci* 1988;50,113-114.
84. Kulkarni AP, Shaikh YR, Dehgan MHGR. Application of neem gum for aqueous film coating of ciprofloxacin tablets. *Int J Applied Res Natural Prod* 2013;6:11-19
85. Oluwatoyin AO. Assessment of albiziazygiagum as a binding agent in tablet formulations. *Acta Pharm* 2005;55:263-276.
86. Pontes PO. Determination of HLB of anacardium gum. *J Pharm* 1971;2:83-91.
87. Zakaria MB, Zainia AR. Rheological properties of cashew gum. *Carbohydr Polym* 1996;29:25-27.
88. Pawar H, D'mello PM. Isolation of seed gum from cassia tora and preliminary studies of its applications as a binder for tablets. *Indian Drugs* 2004;41:465-468.
89. Nayak BS, Nayak UK, Patro KB, Rout PK. Design and evaluation of controlled release bhara gum microcapsules of famotidine for oral use. *Res J Pharm Tech* 2008;1:433-437.
90. Verma PRP, Razdan B. Studies on leucaenaleucocephala seed gum: Emulsifying properties. *J Sci Ind Res* 2003;62:198-206.
91. Verma PRP, Razdan B. Evaluation of leucaenealeucocephala seed gum as suspending agent in sulphadimidine suspensions. *Indian J Pharm Sci* 2003;65:665-668.
92. Verma PRP, Razdan B. Evaluation of leucaenaleucocephalaseed gum in tableting: II. Binding properties in granules and tablets. *S. T. P. Pharma Sci* 2002;12:113-119.
93. Verma PRP, Razdan B. Evaluation of leucaenaleucocephalaseed gum in tableting. I. Disintegrant properties. *S. T. P. Pharma Sci* 2002;12:109-112.
94. Verma PRP, Razdan B. Studies on leucaenaleucocephalaseed gum: Evaluation of suspending properties. *S. T. P. Pharma sci* 2001;11:289-293.
95. Mukherjee B, Dinda SC, Barik BB. Gum cordia: A novel matrix forming material for enteric resistant and sustained drug delivery-A Technical Note. *AAPS Pharm Sci Tech* 2008; 9:330-333
96. De-Foresta H, Michon G. Agroforests in Sumatra, where ecology meets economy. *Agroforestry Today* 1994;6(4):12-13.
97. Senthil V, Gopalakrishnan S, Sureshkumar R, Jawahar N, Ganesh GNK, Nagasamyvenkatesh D. Mucoadhesive slow release tablet of theophylline: Design and evaluation. *Asian J Pharm* 2010;1 64-68.